PU High Build Transparent Basecoat



INCOMPT EVALUATION OF A CONSTRAINT OF A CONSTR	
Technical Data Sheet	TUS162/80 CLEAR POLYURETHANE BASECOAT - HIGH-BUILD Aprenie pena las feer direft der Gest
Area of use:	Flat parts, fitted furniture, solid wood parts, doors.
Method of use:	Spray gun and curtain coater.
Mking procedure:	by weight (kg) by volume (I)
Part A	TU0162/00 100 100
Part B (hardener)	TH0773.00 50 50
Thinner	DE1150100 15-30 15-40
Technical characteristics:	
Solids content (%):	Part A: 48 ± 1
	Pert 8: 28 ± 1
Specific gravity (kg/l):	Part A: 0.960 ± 0.030
	Part B: 0.940 ± 0.030
Vecosity (DIN 4 at 20°C):	PertA: 26" ± 5"
	A+8: 20"±3"
Pol-life:	3 hours
Recommended application weight (pim ²):	Mn. 80 - Max. 200
Interval between coats:	Min. 40" - Max. 3 hours
Number of coats:	Nax 4